



PETRA

COLLECTION

METHODS OF APPLICATION :

Surface of preparation : Pass the sandpaper, dust, chew imperfections and let them dry for at least 4 hours. Apply a coat of PRIMER 100 PT correctly diluted. Drying time is from 4 to 5 hours.

APPLICATION :

There are 2 effects proposed for PETRA :

PIETRA EFFECT :

Apply a thin layer of a few millimeters PETRA BIANCA with a stainless steel trowel. Buffering the surface and let it dry for 6 hours.

There are 2 types of stains :

1- Apply a coat of VELATURA COLORED (eg. VELATURA NERA) with a brush, then apply two coats of SATIN SILVER by choice (eg. Aluminum). Use sponge and live an interval of 2 hours between each application.

2- Apply a coat of FISSATIVO NEUTRO with a brush. Let it dry for 2 hours. Apply two coats of SATIN SILVER COLORED by choice (eg. SATIN SILVER 139 + 300). Use sponge and live an interval of 2 hours between each application.

INDUSTRIALE EFFECT :

Two methods for applying are proposed :

1- CEMENTO EFFECT :

Apply a coat of PRIMER PT100 and scrape off with a wire brush. Let it dry for 2 hours.

Apply PETRA BIANCA with a stainless steel trowel. Draw with a ruler to obtain the desired pattern (squares, rectangles ... etc.), 1 hour is the drying time. Smooth the surface with a stainless steel trowel and apply 2 coats of colored VELATURA, (Ex. Ref. 134).

Use sponge and live an interval of 2 hours between each application.

2- CREATIVITY :

Apply a coat of PRIMER PT100 and scrape off with a wire brush. Let it dry for 2 hours. Apply PETRA BIANCA with a stainless steel trowel. Let it dry for 3 hours. Perform scribing with a tape roller to achieve the desired pattern (squares, rectangles ... etc.). Apply a second coat of PETRA BIANCA with a special trowel to get the desired pattern. Let it dry for 1 hour.

Smooth the surface with a stainless steel trowel. Let it dry for 6 hours. Apply two coats of SATIN SILVER Ref: 303. Use brush and live an interval of 2 hours between each application. The effect CREATIVITY depends on the talent of the applicator.

PACKAGING AND COLOURS :

PRIMER PT 100 : Packaging of 3 - 10 Lt

PETRA BIANCA : Packaging of 5 - 15 Kg

YIELD :

PRIMER PT 100 : 10 m²/Lt

PETRA : 1 m² / 1,5 Kg

VELATURA : 10 m²/Lt

SATIN SILVER : 7 m²/Lt